

AMENDMENTS TO THE CLAIMS

This Listing of Claims will replace all prior versions and listings of claims in this application.

Listing of Claims:

1. (Original) A biodegradable polyester mixture comprising

from 5% to 80% by weight, based on the total weight of components i to ii, of at least one polyester based on aliphatic and aromatic dicarboxylic acids and an aliphatic dihydroxy compound (component i) and

from 20% to 95% by weight, based on the total weight of components i to ii, of at least one renewable raw material (component ii) and

from 0.1% to 15% by weight, based on the total weight of components i to ii, of a glycidyl acrylate and/or glycidyl methacrylate as component iii.
2. (Original) The biodegradable polyester mixture according to claim 1 wherein said component i is polymerized from:
 - A) an acid component comprising
 - a1) from 30 to 99 mol% of at least one aliphatic or at least one cycloaliphatic dicarboxylic acid or its ester-forming derivatives or mixtures thereof
 - a2) from 1 to 70 mol% of at least one aromatic dicarboxylic acid or its ester-forming derivative or mixtures thereof and
 - a3) from 0 to 5 mol% of a sulfonated compound,


the mole percentages of said components a1) to a3) adding up to 100% and

- B) a diol component comprising at least one C₂- to C₁₂-alkanediol or a C₅- to C₁₀-cycloalkanediol or mixtures thereof

and if desired additionally one or more components selected from


- C) a component selected from

- c1) at least one dihydroxy compound which comprises ether functions and has the formula I




where n is 2, 3 or 4 and m is an integer from 2 to 250,

- c2) at least one hydroxy carboxylic acid of the formula IIa or IIb




(IIa)



(IIb)


where p is an integer from 1 to 1500, r is an integer from 1 to 4 and G is a radical selected from the group consisting of phenylene, $-(\text{CH}_2)_q-$, where q is an integer from 1 to 5, $-\text{C}(\text{R})\text{H}-$ and $-\text{C}(\text{R})\text{HCH}_2$, where R is methyl or ethyl,

- c3) at least one amino-C₂- to C₁₂-alkanol or at least one amino-C₅- to C₁₀-cycloalkanol or mixtures thereof
- c4) at least one diamino-C₁- to C₈-alkane
- c5) at least one 2,2'-bisoxazoline of the general formula III




where R^1 is a single bond, a $(CH_2)_z$ -alkylene group, where $z = 2, 3$ or 4 , or a phenylene group

- c6) at least one amino carboxylic acid selected from the group consisting of the natural amino acids, polyamides obtainable by polycondensation of a dicarboxylic acid having from 4 to 6 carbon atoms and a diamine having from 4 to 10 carbon atoms, compounds of the formulae IV a and IVb



where s is an integer from 1 to 1500, t is an integer from 1 to 4 and T is a radical selected from the group consisting of phenylene, $-(CH_2)_u-$, where u is an integer from 1 to 12, $-C(R^2)H-$ and $-C(R^2)HCH_2-$, where R^2 is methyl or ethyl,

and polyoxazolines containing the repeat unit V



where R^3 is hydrogen, C_1 - C_6 -alkyl, C_5 - C_8 -cycloalkyl, unsubstituted or C_1 - C_4 -alkyl-monosubstituted, -disubstituted or -trisubstituted phenyl or is tetrahydrofuryl,

or mixtures of c1) to c6)

and

D) a component selected from

d1) at least one compound having at least three groups capable of ester formation,

d2) at least one isocyanate

d3) at least one divinyl ether

or mixtures of d1) to d3).

3. (Previously Presented) The biodegradable polyester mixture according to claim 1 wherein said component ii is one or more selected from the group consisting of starch, cellulose, lignin, wood and cereals.

4. (Previously Presented) The biodegradable polyester mixture according to claim 1 which comprises

from 10% to 70% by weight of said component i and
from 30% to 90% by weight of said component ii,
each percentage being based on the total weight of said components i to ii.

5. (Previously Presented) The biodegradable polyester mixture according to claim 1 which comprises from 0.5% to 10% by weight of said component iii, based on the total weight of said components i to ii.

6. (Previously Presented) A process for producing biodegradable polyester mixtures according to claim 1 which comprises said components i, ii and iii being in one step mixed and, in the presence or absence of a free-radical initiator, reacted.

7. (Previously Presented) A process for producing biodegradable polyester mixtures according to claim 1, which comprises a first step of said component iii being mixed with and, in the presence or absence of a free-radical initiator, reacted with one of said components i or ii and a second step of the hitherto unused component ii or i being mixed in and reacted.

8. (Canceled).
9. (Presently Presented) Blends, moldings, films, sheets or fibers comprising biodegradable polyester mixtures according to claim 1.
10. (Original) The biodegradable polyester mixture according to claim 2 wherein said component ii is one or more selected from the group consisting of starch, cellulose, lignin, wood and cereals.
11. (Original) The biodegradable polyester mixture according to claim 2 which comprises

from 10% to 70% by weight of said component i and
from 30% to 90% by weight of said component ii,
each percentage being based on the total weight of said components i to ii.
12. (Original) The biodegradable polyester mixture according to claim 3 which comprises

from 10% to 70% by weight of said component i and
from 30% to 90% by weight of said component ii,
each percentage being based on the total weight of said components i to ii.
13. (Original) The biodegradable polyester mixture according to claim 2 which comprises
from 0.5% to 10% by weight of said component iii, based on the total weight of said components
i to ii.
14. (Original) The biodegradable polyester mixture according to claim 3 which comprises
from 0.5% to 10% by weight of said component iii, based on the total weight of said components
i to ii.

15. (Original) The biodegradable polyester mixture according to claim 4 which comprises from 0.5% to 10% by weight of said component iii, based on the total weight of said components i to ii.
16. (Original) A process for producing biodegradable polyester mixtures according to claim 2 which comprises said components i, ii and iii being in one step mixed and, in the presence or absence of a free-radical initiator, reacted.
17. (Original) A process for producing biodegradable polyester mixtures according to claim 3 which comprises said components i, ii and iii being in one step mixed and, in the presence or absence of a free-radical initiator, reacted.
18. (Original) A process for producing biodegradable polyester mixtures according to claim 4 which comprises said components i, ii and iii being in one step mixed and, in the presence or absence of a free-radical initiator, reacted.
19. (Original) A process for producing biodegradable polyester mixtures according claim 5 which comprises said components i, ii and iii being in one step mixed and, in the presence or absence of a free-radical initiator, reacted.
20. (Original) A process for producing biodegradable polyester mixtures according to claim 2, which comprises a first step of said component iii being mixed with and, in the presence or absence of a free-radical initiator, reacted with one of said components i or ii and a second step of the hitherto unused component ii or i being mixed in and reacted.